

Refractory Cement A700

| Chemical Compositions (%) | Items | Specification |
|---------------------------|--|---------------|
| | Al ₂ O ₃ | 50-60 |
| | SiO ₂ | 8 Max |
| | Fe ₂ O ₃ | 2.5 Max |
| | R ₂ O | 0.4 Max |
| Physical Properties | Fineness | |
| | 0.045mm sieve residue (%) | — |
| | Blaine specific surface (m ² /kg) | — |
| | Time of setting | |
| | Initial setting time(h:min) | 0:30 Min |
| | Final setting time(h:min) | 6:00 Max |
| | Flexural strength | |
| | 1d (MPa) | 6.5 Min |
| | 3d (MPa) | 7.5 Min |
| | Compression strength | |
| | 1d (MPa) | 52 Min |
| 3d (MPa) | 62 Min | |

PACKAGE: BIG BAG

All Size and Specifications are Available as Desired by Customers